

Thermal Block Pre-Engineered Metal Building Roof Spacers Comparison Chart

Type of Insulation	Initial R-Value/1"	"Aged" R-Value 180 Days ITTR *1 Per 1"	Warranted R- Value *2 Per 1"	In Service R-Value *3 Per 1"	Compressive Strength *4	Water Absorption CORE % by volume	Water Vapor Permeance (perm)
ASTM	C 578-03				1621	C 272	E-96
Extruded Polystyrene (EXPS)	5.0	5.0	5.0	5.0	25 40 60	.03	1.0
Expanded Polystyrene (EPS)						4.0	5.0
Polyisocyanurate (ISO)	6.25	5.6	5.6	3.85	15 - 20	5	3

*1 Actual verbiage used to describe 180 day R-Value

*2 See manufacturers warranty for impossible stipulations and conditions (READ CLOSE)

*3 Actual materials installed for five years in cavity wall foundation and roofing applications

*4 Fabricated material carries a 25, 40 or 60 PSI